

Article Preview

Materials Science Forum Vols. 730-732 (2013) pp 799-804
 Online available since 2012/Nov/12 at www.scientific.net
 © (2013) Trans Tech Publications, Switzerland
 doi:10.4028/www.scientific.net/MSF.730-732.799

First Principles Calculations and Experiments to Determine the Hydrogenation Process of Cu-Li-Mg

M.H. Braga^{1,2,a}, M.H. Sá^{2,b}, J.A. Ferreira^{3,c}, L.L. Daemen^{1,d}

¹Los Alamos Neutron Scattering Center, Los Alamos National Laboratory, NM, USA

²CEMUC, Engineering Physics Dep., Engineering Faculty, Porto University, Portugal

³LNEG, Laboratório Nacional de Energia e Geologia, S. Mamede Infesta, Portugal

^ambraga@fe.up.pt (corresponding author), ^bmhsa@fe.up.pt, ^cjorge.ferreira@lneg.pt, ^dld@lanl.gov

Keywords: Cu-Li-Mg-H, Density Functional Theory (DFT), Phonons, Neutron Scattering

Abstract. Density Functional Theory (DFT) calculations were performed. They were firstly implemented to optimize the structure and refine the stoichiometry of the only ternary compound, $\text{CuLi}_{0.08}\text{Mg}_{1.92}$ of the Cu-Li-Mg system. Furthermore using DFT, several possible structures of CuMg_2H_x were optimized. Since most of the hydrides are cubic structures or can be considered as distortions of a cubic structure, we have started calculations for CuMg_2H_x ($x = 4 - 6$) with tetragonal and monoclinic structures, similar to those of the hydrides formed by the nearest neighbors of Cu and Mg in the periodic table: NiMg_2H_4 and CoMg_2H_5 (e.g. monoclinic C2/c and tetragonal P4/nmm, respectively). It can be concluded that the most stable configuration corresponds to CuMg_2H_x with C2/c structure. We have performed several neutron scattering experiments that are in agreement with the first principles calculations.

Introduction

Efficient hydrogen storage remains a major technological obstacle toward the development of a hydrogen-based energy economy. We are currently investigating the Cu-Li-Mg-H system. The lighter and cheaper metals and our recent discovery that hydrogen can be reversibly stored in these compounds make them a very attractive alternative to lanthanide-based systems that still constitute Ni-MH batteries nowadays. Preliminary studies at the Los Alamos Neutron Scattering Center (LANSCE) showed that hydrogen unsaturated samples could desorb up to 4.4-5.3 wt% of hydrogen. Experiments furthermore shown that samples containing $\text{CuLi}_x\text{Mg}_{2-x}$ ($x = 0.08$) will start desorbing hydrogen at a temperature from 50 – 130 °C where applications are easier to develop. Hence it should be possible to use this alloy as a hydrogen storage material for fuel cells, batteries and other hydrogen storage devices.

Experimental Methods

Sample Preparation. The Cu-Li-Mg samples were prepared from the pure elements with a target composition of $\text{CuLi}_{0.08}\text{Mg}_{1.92}$. They were prepared by mixing stoichiometric amounts of Cu (electrolytic, 99.99% purity, 325 mesh), Mg (99.8% purity, 200 mesh, Alfa Aesar), and small granules (approx. 2 x 2 x 3 mm) of Li (99% purity, Alfa Aesar). Because of the large vapor pressure of Mg, even below its melting point, the reagents were sealed in a stainless steel crucible in a dry box (He atmosphere). This eliminated possible reagent loss. The samples were heated in a tube furnace with a stirring device to ensure proper mixing of the heterogeneous starting mixture and complete dispersion of Li in the sample. Different reaction temperatures and times were used (from 450 °C for 24h to 1200 °C for 1-2 h). Regardless of reaction conditions, the samples invariably contained Cu_2Mg , CuMg_2 , or both. Nonetheless, we obtained final products containing up to 82.5 at% (77.5 wt%) of $\text{CuLi}_x\text{Mg}_{2-x}$. Since the structure of Cu_2Mg and CuMg_2 is known as well as their hydrogen storage behaviour, this complication translated merely in the refinement of additional phases in the neutron/x-ray powder diffraction patterns. Samples were firstly

All rights reserved. No part of contents of this paper may be reproduced or transmitted in any form or by any means without the written permission of TTP.
www.ttp.net (ID: 193.137.43.157-05/02/13.13:03:30)



HELP

CONTACT US

INFORMATION

TERMS & CONDITIONS

Copyright © 2013 Scientific.net. All rights reserved.